

LUSIA SMOKE



| Specifications | Polished | Matt |
|-------------------------|----------|--------|
| Water Absorption | < 0.05% | < 0.1% |
| Scratch Hardness (Mohs) | 8 | 9 |
| Shade Variation | V1 | V1 |
| DCOF | < 0.4 | > 0.4 |



| Specifications | 12"x24" | 24"x24"* | 24"x48"* |
|----------------|---------|----------|----------|
| Thickness | 9.25 | 9.25 | 9.5mm |
| Width | 300mm | 600mm | 600mm |
| Height | 600mm | 600mm | 1200mm |
| Pcs/Box | 5 | 4 | 2 |
| Random Phases | 16 | 8 | 4 |





2'X2'



12'X24'



24'X24'



24'X48'



2'X2'



12'X24'



24'X24'



24'X48'



32"x64"



2'x2'



12'x24'



24'x24'



24'x48'

| Specifications | 12"x24" | 24"x24" | 24"x48" |
|----------------------|-----------|-----------|-----------|
| Pcs/Box | 5 | 4 | 2 |
| Boxes/Skid | 64 | 40 | 34 |
| Box Weight (lbs/Kg) | 40.3/18.3 | 64.6/29.3 | 68.1/30.9 |
| Skid Weight (lbs/Kg) | 2626/1191 | 2626/1191 | 2361/1071 |
| Dimensions (LxWxH) | 44x36x27 | 43x36x28 | 30x38x52 |

| Characteristic | Value | Test Method |
|--------------------------------------|-------------------------|--------------|
| Water Absorption | ≤0.05% | ISO 10544-3 |
| Apparent Density | >2.28 gm/cc | ISO 51082 |
| Impact Resistance | Min 0.55 | ISO 10545-5 |
| Deep Abrasion Resistance | Max 132 mm ³ | ISO 10545-6 |
| MoH's Hardness | 8 | EN101 |
| Chemical Resistance | No Damage | ISO 10545-13 |
| Stain Resistance | Resistant | ISO 10545-14 |
| Slip Resistance (Friction of Co-eff) | >0.40 | ISO 10545-17 |

