

# SIENA GREY



| Specifications          | Polished | Matt   |
|-------------------------|----------|--------|
| Water Absorption        | < 0.05%  | < 0.1% |
| Scratch Hardness (Mohs) | 8        | 9      |
| Shade Variation         | V1       | V1     |
| DCOF                    | < 0.4    | > 0.4  |



| Specifications | 12"x24"                 | 24"x24"   | 24"x48"* |
|----------------|-------------------------|-----------|----------|
| Thickness      | 9.5mm                   | 9.5mm     | 10mm     |
| Width          | 300mm                   | 600mm     | 600mm    |
| Height         | 600mm                   | 600mm     | 1200mm   |
| Pcs/Box        | 5                       | 4         | 2        |
| Random Phases  | AUTO <sup>1</sup> (>15) | AUTO (>8) | AUTO(>5) |

<sup>1</sup> AUTO random select (X,Y) coordinates randomly and generate unlimited random phases.

\* Special Order Only







2'X2'



12'X24'



24'X24'



24'X48'

| Specifications       | 12"x24"   | 24"x24"   | 24"x48"   |
|----------------------|-----------|-----------|-----------|
| Pcs/Box              | 5         | 4         | 2         |
| Boxes/Skid           | 64        | 40        | 34        |
| Box Weight (lbs/Kg)  | 40.3/18.3 | 64.6/29.3 | 68.1/30.9 |
| Skid Weight (lbs/Kg) | 2626/1191 | 2626/1191 | 2361/1071 |
| Dimensions (LxWxH)   | 44x36x27  | 43x36x28  | 30x38x52  |

| Characteristic                       | Value                   | Test Method  |
|--------------------------------------|-------------------------|--------------|
| Water Absorption                     | ≤0.05%                  | ISO 10544-3  |
| Apparent Density                     | >2.28 gm/cc             | ISO 51082    |
| Impact Resistance                    | Min 0.55                | ISO 10545-5  |
| Deep Abrasion Resistance             | Max 132 mm <sup>3</sup> | ISO 10545-6  |
| MoH's Hardness                       | 8                       | EN101        |
| Chemical Resistance                  | No Damage               | ISO 10545-13 |
| Stain Resistance                     | Resistant               | ISO 10545-14 |
| Slip Resistance (Friction of Co-eff) | >0.40                   | ISO 10545-17 |

